

Number	17-002777-PR03 (NW-K15-09-en-01)
Owner	Follmann GmbH & Co. KG Heinrich-Follmann-Str. 1 32423 Minden Germany
Product	Wood adhesive
Designation	System: 1K-dispersion adhesive Shipping name: FOLCO® LIT D3 W91
Details	Manufacturer Follmann GmbH & Co. KG, - Minden; Hardener -
Special features	-

Result

Classification of thermoplastic wood adhesives for non-structural applications according to EN 204:2016-08



Durability classes: D 3

Average adhesion strength - storage sequence 1 = 11.1 N/mm²

Average adhesion strength - storage sequence 3 = 2.7 N/mm²

Average adhesion strength - storage sequence 4 = 13.0 N/mm²

Basis *)

EN 204:2016-08

*) and corresponding national versions
e.g. DIN EN)

Test report: 17-002777-PR03 PB-
K15-09-de-01

Instructions for use

The results obtained can be used as evidence in accordance with the above basis.

Validity

There is no time limit.

When using this document the up-to-dateness of above basis and the conformity of the product have to be observed.

The data and results given relate solely to the tested/described specimen. This test/evaluation does not allow any statement to be made on further characteristics of the present structure regarding performance and quality.

Notes on publication

The ift-Guidance Sheet "Conditions and Guidance for the Use of ift Test Documents" applies.

ift Rosenheim

18.10.2017



Stefan Hehn, Dipl.-Ing. (FH)
Deputy Head of Testing Department
Laboratory for Material Testing



Andreas Seebauer
Operating Testing Officer
Material Testing

Identity-Check



www.ift-rosenheim.de/ift-geprueft
ID: 56D-A7BE9