



EVEREXCEED AGM TECHNOLOGY

FT12V55

**VALVE REGULATED
LEAD ACID BATTERY (AVR)
FOR COMMUNICATION
STANDBY POWER APPLICATIONS**

12V 55.0AH @ 10 HR RATE to 1.80VPC

12V 54.5AH @ 8 HR RATE to 1.75VPC

12V 168 WATTS/CELL @ 15MIN RATE to 1.67VPC

**LONG
DURATION**



**HIGH
PERFORMANCE**

Innovative Features

- ◆ 12 years design life @ 25°C(77°F);
- ◆ Virgin Pure Lead Tin and thick positive plate technology design for maximum service float life ;
- ◆ UL Recognized component;
- ◆ Valve regulated lead acid battery (VRLA);
- ◆ Optimized high-compression Absorbed Glass Mat (AGM) materials significantly enhance performance and reliability, greater than 99% recombination efficiency;
- ◆ Proprietary Fixed Orifice Plate Pasting technology applying active materials on both sides of the grid for consistent cell -to-cell performance, higher capacity and uniform grid protection.
- ◆ Advanced triple stage unique terminal sealing design to ensure leak free operation;
- ◆ Up to 12 months shelf life due to low self-discharge rate (less than 3%/month at 25°C)
- ◆ Heavy duty M6 / M8 Female copper plated terminals provide maximum performance and easy installation, reduce maintenance and increase safety;
- ◆ Advanced lead high-tin low-calcium alloy, reduces grid corrosion and promotes long battery life;
- ◆ Standard: Reinforced ABS (UL 94HB) container and cover; Optional: Flame-retardant reinforced ABS case and cover compliant with UL94 V-0 with an Oxygen Limiting Index of greater than 28%;
- ◆ Designed to withstand extreme temperature degrees and performance without degradation;
- ◆ Flame arresting, low pressure safety release venting system for individual cells, recognized per UL 924.

12 VOLTS - 55.0 AMPERE HOUR @ 10 HOUR RATE

AH Capacity to 1.80VPC @ 25°C (77°F)

End Point Volts/Cell	1hr	2hr	3hr	4hr	5hr	6hr	8hr	10hr	20hr
1.80	34.1	40.2	44.3	46.8	48.7	51.7	52.5	55.0	59.4

For UPS / Solar / Telecommunication Applications



EverExceed | Empower, Energize, Exceed
the Energy you Expect forever

www.exerexceed.com



Headquarter:

Shenzhen EverExceed Industrial Co., Ltd

① Floor 19, Kechuang Building Hengchangrong High TechPark, Dezheng Road, Shiyao Bao'an District, Shenzhen.

① www.exerexceed.com

① marketing@everexceed.com

Branch Company:

EverExceed International Company Limited (HK)


① 19H Maxgrand Plaza No3 Tai Yau St San PO Kong KLN Hongkong
① info@everexceed.com

EverExceed Corporation Ltd. (UK)

① Unit G25 WaterFront Studios, 1 Dock Road, London, United Kingdom
① Europe@everexceed.com

Electrical Specifications	
Cells Per Unit	6
Voltage Per Unit	12.84V
Weight	38.1lbs 17.3kg
Electrolyte	SG = 1.300
Maximum Discharge Current@5s	660Amps
Short Circuit Current	1600Amps
Internal Resistance	6.5(mΩ)

Length : 280mm
Width : 105mm
Height : 206mm
Total Height : 222mm



Capacity	55.0 Ah @ 10 hr. rate to 1.80 volts per cell @ 25°C (77°F). 54.5 Ah @ 8 hr. rate to 1.75 volts per cell @ 25°C (77°F). 168 Watts per all at the 15 minute rate to 1.67 volts per cell @ 25°C (77°F).
Applicable Operating Temperature Range	-40°C (-40°F) to +70°C (+158°F).
Ideal Operating Temperature Range	+20°C (+68°F) to +28°C (+82.4°F).
Floating Charging Voltage	13.5 to 13.8 VDC/unit Average at 25°C (77°F).
Recommended Maximum Charging Current Limit	13.75 Amperes (0.25C ₁₀ Amperes)
Equalization and Cycle Service Charging Voltage	14.1 to 14.4 VDC/unit Average at 25°C (77°F).
Maximum AC Ripple (Charger)	0.5% RMS or 1.5% P-P of float charge voltage recommended for best results. Maximum voltage allowed = 0.5% RMS (4% P-P). Maximum current allowed = 0.28 amperes RMS (C/10) to 1.80VPC.
Self Discharge	EverExceed FT AGM Range batteries may be stored for up to 12 months at 25°C (77°F) and then a freshening charge is required. For higher temperatures the recharge time interval will be shorter.
Accessories	Inter unit connectors racks and cabinet systems are available.
Terminal: Inserted	Threaded copper alloy insert terminal
Terminal Hardware Initial Torque: Inserted Terminal	5 NM

Constant Power Discharging Ratings - Watts Per Cell @ 25°C (77°F)															
End Point Volts/Cell	5min	10min	15min	30min	45min	60min	End Point Volts/Cell	2hr	3hr	4hr	5hr	6hr	8hr	10hr	20hr
1.80	232	177	147	96	72.8	60.8	1.85	38.9	28.0	22.1	19.5	18.4	12.6	10.6	5.90
1.75	255	190	160	99.3	75.1	62.3	1.80	41.0	29.5	23.3	20.6	19.4	13.3	11.1	6.20
1.67	278	204	168	102	74.4	63	1.75	42.0	30.1	23.7	21	19.8	13.5	11.3	6.30

Constant Current Discharging Ratings - Ampere per Cell @ 25°C (77°F)															
End Point Volts/Cell	5min	10min	15min	30min	45min	60min	End Point Volts/Cell	2hr	3hr	4hr	5hr	6hr	8hr	10hr	20hr
1.80	128	96	82.0	56.4	42.6	34.1	1.85	19.4	13.9	11.1	9.13	8.16	6.36	5.34	2.89
1.75	146	106	89.4	58.3	44.3	35.5	1.80	20.1	14.8	11.7	9.74	8.62	6.57	5.50	2.97
1.67	168	118	97	59.1	44.8	36.0	1.75	20.5	15.1	12.0	9.90	8.94	6.81	5.58	3.03

Note: Batteries to be mounted with 0.39 in (1.00 cm) spacing minimum and free air ventilation.
Specifications subject to change without notification.



EverExceed | Empower, Energize, Exceed
the Energy you Expect forever

www.exerexceed.com



Headquarter:

Shenzhen EverExceed Industrial Co., Ltd

① Floor 19, Kechuang Building Hengchangrong High TechPark,
Dezheng Road, Shiyuan Bao'an District, Shenzhen.

② www.exerexceed.com

③ marketing@everexceed.com

Branch Company:

EverExceed International Company Limited (HK)

④ 19H Maxgrand Plaza No3 Tai Yau St San PO Kong KLN Hongkong
⑤ info@everexceed.com

EverExceed Corporation Ltd. (UK)

⑥ Unit G25 WaterFront Studios, 1 Dock Road, London, United Kingdom
⑦ Europe@everexceed.com